



TEST REPORT

Doc No.-QR/08

Rev. No.-00 Date: 09.04.2018 LRL\02\2018-19\04N

1. Name & Address of Customer

2. Material Identification

3. Sample Condition when Received

4. SRF /Letter Reference

5. Source/Location

6. Date of Sample Receipt

7. Date of Sample Tested

8. Environmental Conditions

: Paharia Minerals

: Fine Aggregate:-M- Sand (1Bag)

: OK.

: SRF Dated 04.04.2018

: -

: 04.04.2018

: 04.04.2018 To 06.04.2018

: As per IS Code

TEST RESULTS

S. No.	Name of Test	Method of Test	Test Result	Unit
1	Water Absorption	IS:2386 (Pt-III)-1963	0.46	%
2	Specific Gravity	15:2300 (Ft-111)-1903	2.62	-
3	Clay, Fine silt & Fine Dust	IS:2386 (Pt-II)-1963	0.80	%

Sieve Analysis

IS Sieve Designations (mm)	Method of Test	Percentage Retained	Cumulative Percentage Retained	Percentage Passing	Requirement as per IS:383-2016, Table-9, Zone-II
10	IS: 2386 (Pt-1) 1963	0.00	0.00	100	100
4.75		1.20	1.20	98.80	90-100
2.36		8.93	10.13	89.87	75-100
1.18		27.60	37.73	62.27	55-90
0.600		10.80	48.53	51.47	35-59
0.300		30.53	79.06	20.94	8-30
0.150		15.33	94.39	5.61	0-10

h Material Testing And Research Laboratory Pvt. Ltd



Page No. 1 of 1

Note:

- This Test Report shall not be reproduced wholly or in part and can not be used as an evidence in the court of law without written approval of M/S Landmark Material Testing And Research Laboratory Pvt. Ltd.
- The results listed refer only to the tested sample and applicable parameters. Endorsement of Product is neither inferred nor implied.
- The sample will be stored up to Three months from the date of issue of test report unless otherwise specified.

Total liability of this laboratory is limited to the invoiced amount.

Regd Office: G-200, RICO Industrial Area, Mansarovar, Jaipur (Raj)-302020